

MY SHIMMERING EYESHADOW CREAM

14.175.02 C155

- Claims:**
- Silicone-free cream-to-powder
 - Comfortable and second skin feel
 - Easy and even application

PHASE	INGREDIENT	INCI NAME	SUPPLIER	%
A	Cetiol® CC	Dicaprylyl Carbonate	BASF	10.00
	Dermofeel® Sensolv	Isoamyl Laurate	Dr Straetmans	8.00
	Lipex® 102	Butyrospermum Parkii (Shea) Butter	AAK	4.10
	Cerabeil Blanche Selection	Beeswax	Baerlocher	4.00
	Cerozo E626	Ozokerite	Baerlocher	5.00
	Lanette® 22	Behenyl Alcohol	BASF	1.50
	Schercemol® DISM	Diisostearyl Malate	Lubrizol	2.00
	Nexbase® 2006 FG	Hydrogenated Polydecene	IMCD	5.00
B	CWD 8906	Hydrogenated Vegetable Oil (and) Titanium Dioxide (CI 77891)	Maprecos	6.00
	CWD 8929	Hydrogenated Vegetable Oil (and) Ultramarines (CI 77007)	Maprecos	6.50
	CWD 8801	Hydrogenated Vegetable Oil (and) Iron Oxide (CI 77491)	Maprecos	2.00
C	Talc Luzenac Pharma M	Talc	Imerys	3.50
	SJ-Touch 1	Polymethyl Methacrylate	Azelis	7.00
	DSPCS/20N-I2	Silica (and) Ethylene/Methacrylate Copolymer (and) Isopropyl Titanium Triisostearate	KOBO	1.00
	MSS 500 W	Silica	KOBO	5.00
	KTZ® Royal Blue	Mica (and) Titanium Dioxide (and) Ferric Ferrocyanide	KOBO	9.00
	KTZ® Misterioso Roussillon	Mica (and) Iron Oxides (CI 77491) (and) Iron Oxides (CI 77499)	KOBO	12.0
KTZ® Misterioso Celandon Red	Mica (and) Titanium Dioxide (and) Iron oxides (CI 77499) (and) Carmine	KOBO	4.00	
D	Biophilic™ H	Hydrogenated Lecithin (and) C12-16 Alcohols (and) Palmitic Acid	Lucas Meyer Cosmetics	4.00
E	Vitapherole® E-1000	Tocopherol (and) Helianthus Annuus (Sunflower) Seed Oil	VitaeNaturals	0.20
	SG 38236	Fragrance	Sozio	0.20

Manufacturing Procedure:

1. Prepare phase A and heat up to 90°C.
2. Prepare phase B, heat up to 90°C. When phase B is homogeneous, pour into phase A.
3. Prepare phase C, add to phase AB under medium stirring until the product is homogeneous.
4. Add D and E just before pouring in packaging.

Formula Specifications:

Aspect: Solid creamy purple eyeshadow
 Viscosity (Rheo ELV 8, spindle 4, 6 rpm, 3 min): NA
 pH: NA
 Preservative efficacy test: NA
 Pilot batch: 41 kg

Stability Tests: On lab batch up to 1 kg
 Up to 1 month at 50°C
 Up to 3 months at: Room Temperature, 4-8°C and 45°C
 Centrifugation (3000 rpm, 20 mn): NA